



MOHM CHEMICAL SDN. BHD. (Co.No.276851-U)
MCX MARKETING SDN. BHD. (Co.No.363532-T)

H.Q. : No.32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor. Malaysia.
Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919
Branch : No.43, Jalan Tambur 33/19, Sek. 33, Shah Alam Technology Park,
47100 Shah Alam, Selangor. Malaysia.
Tel: (60 3) 5124 0876 / 5124 0878 Fax: (60 3) 5124 0877
Email: info@mochem.com Website: www.mochem.com / www.xtraseal.com

TECHNICAL DATA SHEET

x'traseal® CA-288 CONTACT ADHESIVE

DESCRIPTION:

x'traseal® CA-288 is a neoprene adhesive which have medium viscosity, long tack time, easy to apply, cost saving and strong bonding strength.

CA-288 is most suitable for general purpose, light industry, furniture, construction and decoration industry.

Bonding of rubber, wood, plywood, sponge, formic, PVC carpet, cement, metal, cloth and paper product.

PRODUCT SPECIFICATION & PROPERTIES:

APPEARANCE	Brown Yellowish
PRINCIPAL COMPOSITION	Chloroprene Rubber
VISCOSITY	3,000 - 3500cps
SOLID CONTENT	17 - 22%
SPECIFIC GRAVITY	0.89 - 0.92
FLASH POINT	HIGHLY FLAMMABLE

METHOD OF USE:

- ◆ Wipe off moisture, oil and all other foreign matters on bonding surfaces.
- ◆ Apply a thin layer of CA-288 on the bonding surfaces evenly. For effective bonding on absorbent surfaces and porous material normally two coats is required.
- ◆ For bonding surfaces assemble under room temperature the recommended time is 15 to 30 mins.
- ◆ For bonding surfaces with higher absorbent rate the open time shall be shorter but for smooth bonding surfaces the open time shall be longer.
- ◆ After assemble apply suitable pressure on the bonding substrates.
- ◆ Bond strength can be fully obtained after 24 hours.
- ◆ Application should be carried out in a well ventilated area.

STORAGE:

When the adhesive is kept in a well-sealed container and stored in a cool, dry place, a shelf life of the adhesive at least 12 months from date of dispatch can be reasonable expected.

CAUTION:

Avoid breathing in vapor. If in contact with eyes, flush with water for 15 minutes. If swallowed do not induce vomiting. Give a glass of water, and see deliberately inhaling vapours of this product can be harmful or total.

KEEP OUT OF REACH OF CHILDREN